

## TECHNICAL DATA SHEET – MAY 2015

### CPV EDGEBOND

Page 1 of 2  
Version 4  
26/05/2015

## Universal hot melt adhesive for edgbanding machines.

#### Characteristics

CPV EDGEBOND hot melt adhesive is an EVA based synthetic resin with good working properties that can be used on edge banders. The adhesive melts and flows well. It is clean in use and non-stringing. EDGEBOND hot melt adhesive exhibits good bonding properties in connection with decorative laminate edge strips.

The strength and resistance of the bonds depend, among other things, on the percentage of joint surface that has really been bonded. The heat resistance of EDGEBOND adhesive meets all the demands made on furniture in cold, moderate or dry and warm climatic zones.

Heat resistance tested with rising temperature according to a RAKOLL® standard:

Melamine edge strips	approx. 65°C
Polyester laminates	approx. 64°C
Veneers	approx. 65°C

#### Chemical - Technical data:

Base: Ethylene vinyl acetate copolymer  
Viscosity: Approx. 60,000 – 90,000 Cps  
(Brookfield RVT spindle 29, 5 r.p.m, 204 °C)  
Softening point: Approx. 92°C - 99°C  
(Ring & Ball, ASTM E 28)

#### Cleaning

The melting pots should be cleaned at regular intervals since otherwise burnt adhesive will build up on the walls and impair the conduction of heat.

#### Fields of applications:

EDGEBOND hot melt adhesive can be used for most types of edge strips which have been tested by the edge strip manufacturers and approved for the hot melt edgbanding method

#### Edging material

Edge strips have very different adhesive properties, even if material group is the same. For this reason, it is advisable to make tests if the materials are of an unknown type in order to see whether the adhesives can be used.

Pay attention to the recommendations given by the edge strip manufacturers.

#### Instructions for use:

The machine should be adjusted in accordance with the manufacturer's recommendations  
EDGEBOND hot melt adhesive can be processed in the usual way. Good results are obtained under the following conditions:

Room and material temperature: 18 - 20°C  
Wood moisture: 8 - 10 %

**Our Focus is Clear. Perfecting Adhesives.**

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Consolidated Panels & Veneers: 1/7 Millner Avenue, Horsley Park NSW 2175  
Tel: (02) 9604 8100 Email: [sales@cpv.com.au](mailto:sales@cpv.com.au) Web: [www.cpv.com.au](http://www.cpv.com.au)

## TECHNICAL DATA SHEET – MAY 2015

### CPV EDGEBOND

Page 2 of 2  
Version 3  
26/05/2015

Operating temperature at the applicator roll: 190 - 210°C  
Feed speed: at least 20 m/min

The feed speed should be at least 20m/min so that the adhesive does not cool down prematurely and is still fluid enough to wet the entire surface of the

#### Safety recommendations

EDGEBOND is not classified as hazardous according to the NOHSC criteria and no special handling requirements, other than sound industrial hygiene practices, are needed. However, hot melt adhesives release vapours even when the recommended processing temperature is observed. These can irritate the respiratory system. Measures should therefore be taken for the removal of vapours, e.g. by means of an extraction system.

A Material Safety Data Sheet is available from the H.B. Fuller representative or agent in your State.

#### Storage

Store EDGEBOND hot melt adhesive in a cool and dry place

### Made in Australia Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Consolidated Panels & Veneers: 1/7 Millner Avenue, Horsley Park NSW 2175  
Tel: (02) 9604 8100 Email: [sales@cpv.com.au](mailto:sales@cpv.com.au) Web: [www.cpv.com.au](http://www.cpv.com.au)